

ABSTRACT

An article has a characteristic thermal-mechanical stress principal direction. The article has a single crystal substrate having a lowest modulus direction within a target alignment with the principal direction.